

MA300-M

MA300-M is injection a molding aesthetic resin.MA300-M has many properties:(1)anti-scratch(2)high gloss(G60°>85)(3)bright color(4) UV stability(5)light transmittance(6)recycling.MA300-M is mainly used in appearance items of household appliance,etc.

Properties	Standard	Unit	Condition	Typical Value
Physical				
Density	ASTM D792	g/cm3		1.11
Melt Index	ASTM D1238	g/10min	220℃×10kg	20
Mold Shrinkage	ASTM D955	%		0.3~0.6
Gloss	ASTM D523	%		>85
Mechanical				
Tensile Strength	ASTM D638	MPa		55
Flexural Strength	ASTM D790	MPa		70
Flexural Modulus	ASTM D790	MPa		2300
Notched Izod Impact,3.2mm	ASTM D256	J/m	3.2mm,Notched	80
Rockwell Hardness	ASTM D785	R		115
Pencil Hardness	ASTM D2179	/	500g	H
Thermal				
Heat Deflection Temp. 1.82MPa Unannealed	ASTM D648	℃	1.82MPa	83
VICAT	ASTM D1525	℃	B	95
Flammability				
Flammability	UL-94	Class	1.6mm	HB
Electrical Properties				
Volume Resistivity	IEC 60093	Ohm-cm	/	> 1.0E+15
Surface Resistivity	IEC 60093	Ohm	/	> 1.0E+15

For more information please click:www.kumhosunny.com

MA300-M

Processing Parameters	Typical Value	Unit
Drying Temperature	80~85	℃
Drying Time	3~4	hour
Maximum moisture content	0.05	%
Barrel Temperature		
Rear	190~210	℃
Middle	210~220	℃
Front	225~235	℃
Nozzle	225~230	℃
Melt Temperature	220~235	℃
Mold Temperature	60~80	℃
Back Pressure	1~5	MPa
Screw Speed	30~50	rpm

Note:

1)The above data is only for reference. Exact settings have to follow the product,injection machine and mold.

Disclaimer:

To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the data compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or process described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. You may not copy this document to a Web site.

Kumho-Sunny expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication.

For more information please click:www.kumhosunny.com